The Relaxation Behavior of High Chromium- Ni Base Superalloys

Mohamed Nazmy^a and Claus Gerdes^b

Alstom Power Ltd. Baden, CH-5401

^amohamed.nazmy@power.alstom.com

^bclaus.gerdes@power.alstom.com

Keywords: Superalloys, Relaxation, Ni₂Cr intermetallic, Negative creep

Abstract. The relaxation behavior of wrought high chromium Ni-base alloys Nimonic 80A, Nimonic 101 and Nimonic 105 was studied at different temperatures. All of these alloys exhibited increase in the residual stress during the relaxation tests e.g. at 450°C for Nimonic 80A and 650°C for Nimonic 105. The observed increase in the residual stress is a manifestation of the known phenomenon of “negative creep”. The stress free aging of specimens of these alloys exhibited dimensional contraction at different temperatures ranging from 450°C to 650°C. The abnormal relaxation behavior of these alloys and the observed contraction were attributed to the precipitation and ordering of the intermetallic phase Ni₂(Cr,Mo) at the test temperature. The differential thermal analysis i.e. DTA results, demonstrated endothermic peaks to correspond with the order–disorder reaction of Ni₂(Cr,Mo).

Introduction

High chromium Ni-base wrought superalloys such as Nimonic 80A, Nimonic 101 and Nimonic 105 have found extensive use in turbo-machinery applications due to their high strength and corrosion resistance [1-3]. The main strengthening phase in these superalloys is γ' Ni₃(Al,Ti) [3]. Another group of high chromium nickel alloys consists of Hastelloy C-276, Hastelloy C-22HS, Nimonic 75, IN617, IN625, IN686 and Haynes 242, is being used in different components in the power generation industries. The precipitation of intermetallic phases occurs either during aging treatments, or during longtime service. The intermetallic of interest in the high chromium superalloys and nickel-molybdenum alloys is Ni₂(Cr,Mo). This intermetallic is a long-range-order i.e. LRO body centered orthorhombic of the Pt₂Mo type of structure [4]. It has been reported that the binary Ni₂(Cr) experiences a disorder-order transformation accompanied by lattice contraction at ca 590°C [5]. Nevertheless, the critical temperature i.e. T_c of the order-disorder transformation of the intermetallic Ni₂(Cr,Mo) depends on the chemical composition of the alloy [6]. The ordering of this phase gives rise to:- (a) dimensional instability resulting in “negative creep” and (b) changes in the mechanical properties due to increased resistance to dislocations movement.

The aim of the present investigation is:- studying the relaxation behavior, at intermediate temperatures, of the following alloys;- Nimonic 101, Nimonic 105 and Nimonic 80A, and correlate such behavior to the ordering of the Ni₂(Cr,Mo) intermetallic phase.

Materials and Experimental Procedure

The materials used in this investigation were acquired in the form of round bars. Table I gives the nominal composition of the tested alloys and the corresponding heat treatment. The relaxation tests were carried out at a constant total strain $\epsilon_t=0.18\%$. The corresponding residual stress was continuously recorded during the whole duration of the test. Stress free aging experiments were carried out using round specimens of the different alloys, at different temperatures. The specimen dimensions were measured, at different periods, and the corresponding contraction was calculated.

Results and Discussion

The stress relaxation of a specimen of a high chromium Ni-alloy, susceptible to form the Ni_2Cr , is determined by two processes. The first one is the gradual conversion of the elastic strain ε_{el} into plastic strain ε_{pl} , by a creep mechanism as expressed in the following equation:

$$\varepsilon_{\text{el}} + \varepsilon_{\text{pl}} = \text{constant.} \quad (1)$$

The second process is the precipitation and ordering of the intermetallic Ni_2Cr or $\text{Ni}_2(\text{Cr}, \text{Mo})$ that causes the constrained specimen to contract which results in stress increase. These two opposing processes determine the observed relaxation behavior. The stress increase during the relaxation test is a manifestation of the phenomenon of “negative creep”.

The results of the relaxation behavior, at different temperatures, of Nimonic 80A, Nimonic 101 and Nimonic 105 are shown in Figures 1, 2, and 3, respectively. Figure 4, gives the results on aging, at different temperatures, of the three alloys of interest.

The residual stress of Nimonic 80A, as given in Fig. 1, exhibited a clear increase as a function of time in the case of at 450°C and normal stress relaxation trend at 600°C and 650°C . Nimonic 80A exhibited a significant contraction at 450°C as shown in Fig. 4. This contraction is due to the formation and ordering of Ni_2Cr . These results agreed very well with what was reported in ref. 8. The amount of contraction in Nimonic 80A depends on the aging temperature and time [8].

In the case of Nimonic 101, the residual stress exhibited a significant increase with test duration at 650°C and normal decrease in stress relaxation at 700°C , as shown Fig.2. Nevertheless, the residual stress at 600°C exhibited a small dip at the beginning of the test followed by moderate stress increase. This is due to the enhancing effect of stress and temperature on the kinetics of ordering of $\text{Ni}_2(\text{Cr}, \text{Mo})$ intermetallic as reported in ref. 9 for the high chromium and molybdenum IN686 alloy. The contraction of Nimonic 101 on aging at 500°C and 600°C is shown in Fig. 4 and is attributed to the precipitation and ordering of the intermetallic $\text{Ni}_2(\text{Cr}, \text{Mo})$. The contraction of the solution treated and water quenched Nimonic 101 specimen is given in Fig.4 as well. The contraction in this specimen is significantly larger than that of the specimens in the fully heat treated condition, since this contraction is due to the precipitation of both γ' i.e. $\text{Ni}_3(\text{Al}, \text{Ti})$ and the ordering of $\text{Ni}_2(\text{Cr}, \text{Mo})$. The DTA curve on Fig. 5, shows an endothermic peak at ca 660°C , of an aged Nimonic 101 specimen, due to the order- disorder reaction in this alloy.

The relaxation behaviors of Nimonic 105 at 650°C and 700°C are given in Fig. 3. The residual stress exhibited an increase during the test at 650°C . This is again due to the precipitation of the LRO $\text{Ni}_2(\text{Cr}, \text{Mo})$ and further precipitation of γ' particles. At 700°C test, the residual stress showed an increase followed by a gradual decrease. This behavior could be due to the slow disordering of the $\text{Ni}_2(\text{Cr}, \text{Mo})$ phase in this alloy, and the increase in the creep strain at 700°C . According to ref. 6 the T_c of the intermetallic phase in a certain alloy depends on the chemical composition of that alloy. Specimens of Ni_2Cr & $\text{Ni}_2(\text{Mo}, \text{Cr})$ intermetallic phases were prepared by button arc melting for DTA investigations. Fig. 5 shows the DTA results of aged Nimonic 101, and the stoichiometric intermetallics Ni_2Cr and $\text{Ni}_2(\text{Cr}, \text{Mo})$. The result on contraction of Nimonic 105 is given in Fig. 4.

Conclusions

- (1) Nimonic 80A, Nimonic 101 and Nimonic 105 alloys exhibited increase in the residual stress during relaxation testing at different temperatures as a manifestation of “negative creep”.
- (2) The same alloys exhibited dimensional contraction during stress free aging at different temperatures due to the precipitation and ordering of the intermetallic phase $\text{Ni}_2(\text{Cr},\text{Mo})$.
- (3) The DTA results showed endothermic peak at ca 650°C to correspond with the order-disorder reaction of the intermetallic phase.
- (4) The observed unusual relaxation behaviors, at different temperatures, of the high chromium Ni base superalloys i.e. Nimonic 80A, Nimonic 101 and Nimonic 105 should be taken into consideration on designing components e.g. bolts & springs for high temperature applications.

Acknowledgement

The authors would like to express their appreciation to A.Künzler for his diligent technical assistance during the course of the present investigation.

References

- [1] K.H.Mayer and K.H.Keinburg, “Operating Experience and Life Span of Heat-Resistant Bolted Joints in Steam Turbines of Fossil-Fired Power Stations”, in I Mech. E., C221/80, 1980.
- [2] M.S.Loveday and B.F.Dyson, “Prestrain-Induced Particle Microcracking and Creep Cavitation IN 597”, in Acta Metall. Vol. 31. No 3,pp 397-405, 1983.
- [3] E.Metcalf, B. Nath and A. Wickens, “ Some Effects of the Ordering Transformation in Nimonic 80A on Stress Relaxation Behaviour”, in Materials Science and Engineering, 67, pp. 157-162, 1984.
- [4] H.M.Tawancy, “Order-Strengthening in a Nickel-Base Superalloy (Hasselloy Alloy S)”, in Metall. Trans.A Vol. 11A, pp.1764-1765, 1980.
- [5] A.Marucco and B.Nath, “Effect of ordering on the properties of Ni-Cr alloys”, in Journal of Materials Science 23, pp.2107-2114, 1988.
- [6] D.Blavette, E.Cadel and B.Deconihout,”The Role of the Atom Probe in the Study of Nickel-Based Superalloys”, in Materials Characterization 44, pp.133-157, 2000.
- [7] E.Lang, V.Lupinc and A Marucco, “Effect of Thermomechanical Treatments on Short-range Ordering and Secondary-phase Precipitation in Ni-Cr based Alloys”, in Materials Science and Engineering, A114, pp.147-157, 1989.
- [8] A.Marucco, “Effect of Composition on The Order-Disorder Transformation in Ni-Cr Based Alloys”, in Key Engineering Materials Vols.48, pp.77-90, 1990.
- [9] Kaori Miyata, “Effect of Hydrogen Charging on Dislocation Behavior in Ni-Cr and Ni_2Cr Alloys”, in Metall. Trans. A 34A, pp.1249-1257, 2003.

Table1: Chemical composition in wt % and heat treatment of Ni-base alloys & superalloys

Alloy	Ni	Cr	Co	Mo	W	Ta	Nb	Al	Ti	Fe	Mn	Si	C
Nimonic80A	76	19,5	-	-	-	-	-	1,4	2,4	-	0,3	0,3	0,06
Nimonic101	48	24,5	10	10	-	-	1	1,5	3	-	-	-	0,05
Nimonic105	53	15	20	5	-	-	-	4,7	1,2	-	0,3	0,3	0,13

Nimonic 80A: 1080°C/8h/AC + 705°C/16h/AC

Nimonic 101: 1100°C/4h/AC + 850°C/16h/AC

Nimonic 105: 1150°C/4h/AC + 1050°C/16h/AC + 850°C/16h/AC

Fig. 1: Relaxation behavior of Nimonic 80A, $\varepsilon_t = 0.18\%$

Fig. 2: Relaxation behavior of Nimonic 101, $\varepsilon_t = 0.18\%$

Fig. 3: Relaxation behavior of Nimonic 105, $\varepsilon_t = 0.18\%$

Fig. 4: Dimensional contraction of Ni-base alloys at different temperatures

Fig. 5: DTA curve of aged Nimonic 101, Ni_2Cr and $\text{Ni}_2(\text{Cr}, \text{Mo})$