Catalytic Activity of Ni₃Al Foils in Methanol Reforming

P. Jozwik^{1,a}, R. Grabowski² and Z. Bojar^{1,b}

¹ Military University of Technology, Department of Advanced Materials and Technology
Kaliskiego 2 St., 00-908 Warsaw 49, Poland.

² Institute of Catalysis and Surface Chemistry PAS, Niezapominajek 8 St., 30-239 Cracow, Poland.

^apjozwik@wat.edu.pl, ^bzbojar@wat.edu.pl

Keywords: Ni₃Al intermetallic alloy, Thin foils, Methanol decomposition, Hydrogen production, Carbon nanofibres

Abstract. Intermetallic Ni₃Al-based alloys (doped with zirconium and boron) represent a group of advanced materials with potential outstanding physical and chemical properties (such as high catalytic activity and structural stability in corrosive environments) that make them a considerable candidate for many high-tech applications. In this paper, the catalytic activity of fully dense Ni₃Al-based thin foils (as thin as 50 µm) possessing structures with micrometer or nanometer grain sizes is discussed. The examined material, without any additional catalytic coating, was successfully produced from as-cast coarse-grained sheets by heavy cold rolling and recrystallisation with an appropriately chosen set of parameters. The examination focuses on methanol and methanol/water mixture decomposition into H₂ and CO at temperatures up to 530°C in a quartz reactor. Except for these products, a small amount (below 1%) of CO₂ and dimethyl ether was observed. The catalyzed reaction began effectively at about 400°C, with a methanol conversion of about 90% or higher.

Introduction

Ordered Ni₃Al intermetallic alloys constitute a unique class of metallic materials that show excellent oxidation/corrosion resistance, fairly high melting temperatures, relatively low densities and anomalous strengthening with increasing temperature [1,2].

With respect to the above-mentioned properties of Ni₃Al alloys, the applications of thin foils may take a special rank. These materials can be used in high-performance applications in the form of honeycomb structures, which have the advantages of light weight, high stiffness and high strength, as compared to bulk Ni-based superalloys. Thus far, we have successfully fabricated thin Ni₃Al foils by cold rolling commonly casted ingots without additional treatment. The proposed technology allows us to obtain foils with a thickness below 50 µm, with micro and nanostructures [2,3]. Another method for obtaining thin foils (with microcrystalline structures only) was reported by Hirano et al. [4], where directionally solidified ingots were rolled at room temperature. For materials obtained according to this method, the authors confirmed good catalytic properties in methanol decomposition [5,6].

Methanol is expected to be used as an alternative energy source (as a fuel) in the near future because it can be synthesized from biomass, natural gas, coal, etc., which are more abundant than crude oil [6-8]. Additionally, methanol decomposition to hydrogen and carbon monoxide is an endothermic process, and therefore, it allows for the possibility of recovering waste heat from industrial and automobile exhaust gases. Integrated heat-exchanger/reactors can possibly be used to realise this new processing concept – connecting exothermic combustion with endothermic methanol decomposition. The above-mentioned properties of thin Ni₃Al foils, in particular, their good catalytic properties in the absence of any coating, allow micro-scale power sources (e.g., MEMS, MECS) to be built with energy densities exceeding those of macro-scale devices [9-15].

The main aim of this work is to investigate the influence of Ni₃Al foil structures (nano and microstructures) on methanol decomposition and to further verify the catalytic activity of materials obtained by author's method [2,3], which differs from that described in the present literature [5,6].

Experimental

A nearly single-phase Ni_3Al intermetallic alloy with the nominal composition of Ni–22,1Al–0,26Zr–0,1B (at.%) was induction-melted from pure elements in high purity argon and cast into a shell mold. The obtained ingot was cut into sheets using a friction saw.

The microcrystalline foils were obtained by cold rolling at room temperature for 95% cold work without intermediate annealing. For the next step, the prepared material was recrystallisation-treated up to 1100°C for up to 1.5 hours in an argon atmosphere. The nanocrystalline foils were obtained by cold rolling at liquid-nitrogen temperature for 98% cold work and were subsequently annealed up to 700°C for 15 min in an argon atmosphere. More information about the fabrication procedures has been given previously [2,3]. Ni_3Al foils (in micro and nanocrystalline conditions) obtained by the above-mentioned processing technology were mechanically polished for the next step.

Catalytic experiments of hydrogen production from methanol were performed in a fixed-bed quartz tube reactor. Foils with thickness about 60 μm , mechanically cut into small pieces (6 x 2 mm, total weight 0.4 g per each experiment). Before the catalytic experiments, the foils were annealed in a reducing atmosphere, as described in the current literature [5,6]. The initial feed mixtures with different feed compositions (methanol, water and helium) were introduced into the reactor at a flow rate of 30 ml/min (1.8 l/h). Feed mixtures were obtained by flowing helium through a known mixture of water and methanol at 25°C (Tab. 1).

Table 1. The mixtures of MeOH - water that were used to examine methanol decomposition

Designation	Methanol content in liquid phase [%]	Calculated partial pressure in gas phase at 25°C [kPa]		MeOH/ H_2O partial pressure ratio
		MeOH	H_2O	
K 100	100	17.4	0	-
K 95	95	15.6	0.4	39

The catalytic experiments were carried out at temperatures ranging from 280°C to 530°C . The temperature was elevated every 30 min by 50°C , and the products were analysed on-line by a Quadera 200 mass spectrometer. The yield and selectivity were estimated, using calibration coefficients obtained from an analysis of a known mixture.

Selectivity to a particular product was calculated as the number of moles of the particular product to the sum of all of the product moles, expressed as a percentage. However, the yield of a particular product was calculated as the product of the ratio of methanol conversion and selectivity to the particular product.

The surface morphologies, examined after catalysis, were observed by scanning electron microscopes, Phillips XL 30 and Zeiss Leo 1530, both with secondary electron detectors (SE).

The phase structure of the surface products after catalysis was examined by X-ray diffraction using a Seifert 3003 diffractometer with CuK_α radiation. Spectral interpretation was carried out using Seifert Analyze software and the DHN PDF 2 database.

Results and discussion

Catalytic results. As can be seen in Fig. 1, regarding microcrystalline Ni_3Al , the conversion of pure methanol ("K100" – Tab. 1) with increasing temperature is generally rapid and begins at approximately 280°C . At about 430°C , the value of methanol conversion reaches about 90%, and at temperatures greater than 480°C , it stabilises at nearly 100% (98,7%) after only 120 min. The addition of water to the feed mixture changes the temperature dependence of the conversion. An increase in the water content in the mixture improves the conversion. Small amounts of water (~5%) result in a small improvement in the methanol decomposition - the process begins earlier and reaches a level of 98% at temperatures above 430°C . This is in contrast to the recent literature, where a comparable level of conversion (98%) [5, 6] was obtained at a higher temperature - about 520°C - for 29 hours. At temperatures similar to those used in our experiment (about 440°C), the authors of the above-cited literature obtained less than 80% methanol conversion for 65 hours.

On the basis of the results depicted in Fig. 1, only the pure methanol and methanol with a 5%vol addition of water were chosen for the catalytic experiments with nanocrystalline Ni_3Al foils. In these two cases, the calculated partial pressure of MeOH in the feed mixture composition was 17,4 kPa MeOH for pure methanol and 15,6 kPa MeOH for the feed mixture with the added water. Figure 1b shows the results of MeOH conversion on nanocrystalline foils as a function of temperature. As can be seen in Fig. 1b, in comparison to the microcrystalline Ni_3Al catalyst, at temperatures lower than 330°C , the conversion of MeOH is practically zero. The reaction starts above 330°C and develops quickly with increasing temperature. The addition of a small amount of water (5%) slightly changes the course of conversion, and the process ends at a level of nearly 100%.

Fig. 1. Conversion of methanol for different feed mixture compositions as a function of temperature on Ni_3Al micro (a) and nanocrystalline (b) foil catalysts (described in Tab. 1).

In Fig. 2a and 2b, the selectivities to the main products obtained on the micro and nanocrystalline foils are shown. For both feed mixture compositions, CO and H_2 are the main products, and for the case of the microcrystalline Ni_3Al catalyst, we observed similar curves for both feed mixtures. Whereas for nanocrystalline foils, the relative concentration of CO and H_2 depends on the feed mixture composition and can be easily observed at temperatures above 400°C – the selectivity of hydrogen in these conditions was even higher than the selectivity of carbon monoxide.

Fig. 2. Selectivity to the main products (H₂, CO, DME, and CO₂) for the two feed mixture compositions (open markers and solid lines – pure methanol: “K100”, gray markers and dotted lines – methanol + 5% water: “K95”) as a function of temperature for Ni₃Al microcrystalline (a) and nanocrystalline (b) foils.

The clean and lustrous surfaces of the Ni₃Al foils, as observed before the experiment, are covered with a film substance that looks like soot after the catalytic examination. The surface SEM observations show the presence of carbon nanofibres and metal-like contrast nanoparticles, deposited during methanol decomposition (Fig. 3 and 4). The microcrystalline foils observed in the secondary electron (SE) mode possess individual carbon nanofibres with a predominant average diameter below 50 nm (Fig. 3). For the case of the nanocrystalline foils, we observed different (microcrystalline) shapes and nanofibre dimensions. A bimodal size of carbon nanofibres was visible – well twisted, relatively thick fibres of about 120 nm in diameter and smaller ones of about 30 nm (Fig. 4). For both cases of material structures, we obtained carbon nanofibres much smaller than those reported in the literature [5,6]. The metal-like nanoparticles were found to be nanoparticles of pure nickel built in a carbon nanofibre structure. The existence of both discussed components on the foil surfaces after the decomposition reaction, for example, on the Ni₃Al microcrystalline foil, was confirmed by X-ray diffraction analysis (Fig. 5). Metal-like nanoparticles are visible even in SE images at large magnification (for example, Fig. 3b).

Fig. 3. Morphology of carbon nanofibres (SEM - SE) deposited on the surface of Ni₃Al microcrystalline foils after 150 min of reaction in pure methanol (sample “K100”- Tab. 1).

Fig. 4. Morphology of carbon nanofibres (SEM - SE) deposited on the surface of Ni₃Al nanocrystalline foils after 150 min of reaction in pure methanol (sample “K100”- Tab. 1)

The X-ray diffraction patterns for reaction products scraped from the Ni₃Al foil (Fig. 5) demonstrated that the catalytic reaction products contain only pure nickel and graphite. The small nickel particles, probably formed in accordance with the mechanism described in previous reports [6], must serve as an effective catalyst for methanol decomposition, as well as carbon nanofibres, which are expected in common catalyst supports due to their large edges. We also observed that the nanocrystalline Ni₃Al foils possess a higher amount of nickel particles than their microcrystalline counterparts. This probably results in better catalytic properties for the nanocrystalline materials.

Fig. 5. X-ray diffraction patterns of products scraped off of the surface of Ni₃Al microcrystalline foils after 150 min of reaction in pure methanol

Conclusions

Thin Ni₃Al foils with micro and nanocrystalline structures demonstrated good catalytic properties in methanol decomposition in a temperature range of 380-580°C. The existence of carbon nanofibres and nickel nanoparticles forming spontaneously on the foil surfaces during the catalytic reactions was observed. Our main results can be summarised as follows.

1. The methanol conversion to H₂ and CO over flat lustrous Ni₃Al foil surfaces begins at about 280°C for a microcrystalline substrate structure and at about 330°C for a nanocrystalline structure.
2. A small addition of water (5%) to the feed mixture positively influences the methanol conversion on both the micro and nanocrystalline Ni₃Al catalysts and also has an important influence on the

selectivity to H₂ and CO. For the nanocrystalline foils, we observed a selectivity to H₂ that is higher than that to CO, while the opposite trend was observed in the microcrystalline counterparts.

3. Selectivity to the side products (CO₂, DME) is very small and decreases with reaction temperature.

Acknowledgement

The authors gratefully acknowledge financial support for the years 2008-2010 from the Polish Ministry of Science and Higher Education (OR00004905 and R0702502).

References

- [1] V. K. Sikka, S. C. Deevi, S. Viswanathan, R. W. Swindeman, M. L. Santella: *Intermetallics* (2000), No. 8.
- [2] P. Jóźwik, Z. Bojar: *Archives of Metallurgy and Materials* (2007), 52, 321-327.
- [3] Z. Bojar, P. Jóźwik, J. Bystrzycki: *Scripta Materialia* (2006), 55, 399-402.
- [4] M. Demura, K. Kishida, Y. Suga, M. Takanashi, T. Hirano: *Scripta Materialia* (2002), No. 47.
- [5] D. H. Chun, Y. Xu, M. Demura, K. Kishida, D. M. Wee, T. Hirano: *Journal of Catalysis* (2006), 243, 99 – 107.
- [6] D. H. Chun, Y. Xu, M. Demura, K. Kishida, M. H. Oh, T. Hirano, D. M. Wee: *Catalysis Letters* (2006), 106, 71 – 75.
- [7] G. W. Crabtree, M. S. Dresselhaus, M. V. Buchanan: *Physics Today* (2004), 12, 39-44.
- [8] G.W. Huber, J.W. Shabaker, J.A. Dumesic: *Science* (2003), 300, 2075-2077.
- [9] J. Sehested: *Catalysis Today* (2006), 111, 102-110.
- [10] K. F. Jensen: *Chemical Engineering Science* (2001), 56, 293-303.
- [11] G. Kolb, J. Schurer, D. Tiemann, M. Wichert, R. Zapf, V. Hessel, K. Lowe: *Journal of Power Sources* (2007), 171, 198-204.
- [12] T. Kim, S. Kwon: *Chemical Engineering Journal* (2006), 123, 93-102.
- [13] K. F. Jensen: *Chemical Engineering Science* (2001), 56, 293-303.
- [14] T. Kim, S. Kwon: *Journal of Micromechanics and Microengineering* (2006), 16, 1760-1768.
- [15] T. Kim, S. Kwon: *Chemical Engineering Journal* (2006), 123, 93-102.
- [16] W. Cheng, Ch. Shiau, T. Liu, H. Tung, H. Chen, J. Lu, Ch. Hsu: *Applied Catalysis B: Environmental* (1998), 18, 63-70.